

FS-G7747

Ruban de parement ALPHA VR-R-PLUS

Le FS-G7747 est un ruban de parement renforcé, composé de pellicule de polypropylène, de canevas et de polyester métallisé. Combiné à un adhésif acrylique à base de solvant de grande efficacité à basse température, il comprend une doublure antiadhésive en silicone facile à enlever, et offre une adhésion rapide supérieure à des températures d'utilisation normales ainsi qu'une grande efficacité à basse température.

Applications

- Pare-vapeur / joint de vapeur pour isolant ALPHA-VR-R-PLUS.

Caractéristiques

- Adhésif d'une grande efficacité
- Bonne capacité adhésive au polypropylène
- Excellent pare-vapeur et excellent coefficient de transmission de vapeur d'eau

Storage & Usage Conditions

Store tape in its original packaging away from direct sunlight and in a cool and dry area. For optimum performance, tape should be used within 12 months of date of shipment. Tape works best when applied to a surface that is clean, dry and free of grease, oil or other contaminants.

Épaisseur	8,5 mils
Épaisseur du support	7,8 mils
Résistance à la rupture	42 lb/po
Adhésif	Acrylique
Capacité adhésive	40,0 oz/po
Température d'application	-20 °C à 48 °C (-4 °F à 104 °F)

Température de service	-40 °C à 80 °C (-40 °F à 176 °F)
Allongement à la rupture	1,0 %

The information cited is in good faith and has been established from sources held to be secure and reliable. The values listed are typical properties. Individual rolls may vary slightly from these values. All ECHOTape products are warranted to be free of defects at time of shipment. Many factors can affect the use and performance of a product in a particular application and the user must, by test or otherwise, determine suitability for purpose; Edelstein makes no representation or warranty, express or implied, concerning any application and usage of its products. If ECHOTape product is proved to be defective, the exclusive remedy, shall be for Edelstein to replace the defective product. ECHOTape shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including but not limited to, contract, negligence, warranty or strict liability.